

Flowgrip HD

Product sheet

Product description

Flowgrip HD is a three-component, solvent-free, polyurethane-based primer and binding agent.

Uses

Flowgrip HD is used as a binding agent for decorative, hard wearing aggregates. Flowgrip HD accepts aggregate scatter to produce an anti-skid surface. Flowgrip HD can also be used as a primer and/or scratch-coat on concrete and asphalt.

Environment & Health

Flowgrip HD is a solvent free product and practically odourless during application. Follow the appropriate Occupational Health and Safety guidelines applicable to the location where the application is undertaken. For more information, please refer to the safety datasheets for the individual components.

Ratio of components

The product is supplied in full units as A+B+C. Do not split the compounds/components as this may jeopardise the end result.

Add all of Hardener B to Base A and mix before adding Filler C. Ensure that all Filler C is mixed in from the sides of the container and fully dispersed throughout the mix. Mix with slow speed drill and helical spinner, taking care not to entrain air.

Application temperature

The recommended substrate temperature is 10 - 25°C, but no less than 5°C.

The temperature of the substrate should exceed the "dew point" by 3°C during application and hardening. Temperatures should not fall below 5°C in the 24hrs after application.

Application time/pot life

Ready-mixed product should be used within 20 minutes at a temperature of 20°C. At higher temperatures the application time is shorter.

Curing time (at 20°C)

Tack free after 5 hours (10 hours at 10°C).

Can be walked on after 16 hours (30 hours at 10°C).

Maximum overcoat time 24 hours (36 hours at 10°C).

Full traffic after 24 hours (36 hours at 10°C).

The product is fully hardened after 5 - 7 days.

High humidity in the early stages of cure can result in white, matt surfaces (blooming). Do not cover or wash within the first 24 hours of curing.

Colours

Natural

Solids content

Approx. 100 %

Finish

Gloss

Density

Component A approx. 1.6 kg/l

Component B approx. 1.3 kg/l

Component C approx. 2.65 kg/l

A+B+C approx. 1.8 kg/l.

Storage

12 months in unopened pack.

Storage temperature between 5°C and 40°C.

Protect from weather and moisture/contaminant ingress.

Packaging

The product is delivered A+B in the following packs.

Unit		Base A	Hardener B	Filler C
30 kg	(16.7 litres)	18.3 kg	4.1 kg	7.6 kg

Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

2014.07, 05 UK