

Peran LF

Product sheet

Product description

Peran LF is a 2-component, epoxy-based elastic product with the addition of a specially selected filler. Peran LF produces a surface with low friction.

Uses

Peran LF is used as a surface layer on skid training courses, i.e. as surface coatings intended to correspond to slippery road surfaces in winter.

Environment & Health

Peran LF is a solvent and Nonyl Phenol free product, and practically odourless during application. Follow the appropriate Occupational Health and Safety guidelines applicable to the location where the application is undertaken.

For more information, please refer to the safety datasheets for the individual components.

Ratio of components

3.3 parts of component A is mixed with 1 part of component B and 4.3 parts of component C, by weight.
2.8 parts of component A is mixed with 1 part of component B and 2.3 parts of component C, by volume.

Add all of Hardener B to Base A. Mix with slow speed drill and helical spinner, taking care not to entrain air.

Application temperature

The recommended substrate temperature is 15-25°C. The temperature of the substrate should exceed the "dew point" by 3°C during application and hardening.

Temperatures should not fall below 5°C in the 24 hrs after application.

Application time/pot life

Ready-mixed product should be used within 30 minutes at a temperature of 18°C. At higher temperatures the application time is shorter.

Curing time (20°C)

Can be overcoated after 15 hours.

Can be walked on after 15 hours.

Maximum overcoat time 24 hours

The product is fully hardened after 5-7 days.

High humidity in the early stages of cure can result in white, matt surfaces (blooming).

Do not cover or wash within the first 16 hours of curing.

Colours

Grey

Solids content

Approx. 100 %

Finish

Gloss

Density

Component A approx. 1.25 kg/l.
Component B approx. 1.05 kg/l.
Component C approx. 1.85 kg/l.
A+B+C approx. 1.60 kg/l.

Storage

12 months in unopened pack at a temperature of 5-40°C.
Protect from weather and moisture / contaminant ingress.

Packaging

The product is delivered A+B+C in the following packs:

Unit	Base A	Hardener B	Filler C
22.4 kg (14 litres)	8.6 kg	2.6 kg	11.2 kg

Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.